



# Industrial Research Services

Materials Science & Engineering, Graham Road (PO Box 56), Highett, Victoria, Australia 3190  
Telephone: 61 3 9252 6000 Facsimile: 61 3 9252 6244 Email: tiles@csiro.au Web: <http://www.cmse.csiro.au>

## Registered Testing Authority - CSIRO

27 January 2009

Our Ref. EN13 / 1667 03/0212

### TEST REPORT No. 4686.2s

Requested by: Dalsouple Australia Pty Ltd  
on (date): 14 January 2009  
Manufacturer: Dalsouple Australia Pty Ltd  
Product Desc.: Endura rubber flooring, Black, sculptured profile  
460x460mm

Sampling details:  
Where: Delivered  
Date: 14 January 2009  
By whom: Courier  
How (methods): N/A

The results reported relate only to the sample(s) tested and the information received. No responsibility is taken for the accuracy of the sampling unless it is done under our own supervision. CSIRO cannot accept responsibility for deviations in the manufactured quality and performance of the product. While CSIRO takes care in preparing the reports it provides to clients, it does not warrant that the information in this particular report will be free of errors or omissions or that it will be suitable for the client's purposes. CSIRO will not be responsible for the results of any actions taken by the client or any other person on the basis of the information contained in the report or any opinions expressed in it. The reproduction of this test report is only authorised in the form of a complete photographic facsimile. Our written approval is necessary for any partial reproduction.

This test report consists of 4 pages

#### SUMMARY OF SLIP RESISTANCE TESTS PERFORMED:

		Result	Class
AS/NZS 4586:2004	Slip resistance classification of new pedestrian surface materials Appendix A: WET Pendulum (Four S slider):		
	Mean BPN:	10	Z [LOW*]
AS/NZS 4586:2004	Slip resistance classification of new pedestrian surface materials, Appendix D: OIL-WET Ramp		
	Mean overall acceptance angle:	10.4°	R 10 [LOW*]

\* = CSIRO classification

In order to interpret the classifications, please refer to Standards Australia Handbook 197, An Introductory Guide to the Slip Resistance of Pedestrian Surface Materials, which recommends minimum classifications for a wide variety of locations.

It is important to realise that test results obtained on unused factory-fresh samples may not be directly applicable in service, where proprietary surface coatings, contamination, wear and subsequent cleaning all influence the behaviour of the pedestrian surface.

REPORT NO: 4686.2s  
 ISSUE DATE: 27 January 2009  
 MANUFACTURER: Dalsouple Australia Pty Ltd  
 PRODUCT DESC: Endura rubber flooring, Black, sculptured profile  
 460x460mm

Page 2 of 4

**SLIP RESISTANCE CLASSIFICATION OF NEW PEDESTRIAN SURFACE MATERIALS**

**WET PENDULUM TEST METHOD**

TEST CARRIED OUT IN ACCORDANCE WITH  
 AS/NZS 4586:2004 (Appendix A)

Test Date: 16 January 2009

RESULTS: Location: Slip Resistance Laboratory Rubber slider used: Four S  
 Conditioned with grade P400 paper, dry  
 Sample: Unfixed  
 Cleaning: Distilled water  
 Temperature: 23°C

Pendulum Friction Tester: Munro-Stanley (S/N: 9234, calibrated 13/09/07)  
 Test conducted by: Gerald Fisher

	Specimen				
	1	2	3	4	5
<b>Last 3 swings</b>	<b>10</b>	<b>11</b>	<b>11</b>	<b>10</b>	<b>10</b>
	<b>10</b>	<b>11</b>	<b>10</b>	<b>10</b>	<b>10</b>
	<b>10</b>	<b>10</b>	<b>10</b>	<b>9</b>	<b>9</b>
<b>Averages</b>	<b>10</b>	<b>11</b>	<b>10</b>	<b>10</b>	<b>10</b>

**Mean BPN : 10**

**CLASS :**

**Z [LOW\*]**

\* = CSIRO classification



# Industrial Research Services

Materials Science & Engineering, Graham Road (PO Box 56), Highett, Victoria, Australia 3190  
Telephone: 61 3 9252 6000 Facsimile: 61 3 9252 6244 Email: tiles@csiro.au Web: http://www.cmse.csiro.au

REPORT NO: 4686.2s  
ISSUE DATE: 27 January 2009  
MANUFACTURER: Dalsouple Australia Pty Ltd  
PRODUCT DESC: Endura rubber flooring, Black, sculptured profile  
460x460mm

Page 3 of 4

## SLIP RESISTANCE CLASSIFICATION OF NEW PEDESTRIAN SURFACE MATERIALS

### OIL-WET RAMP TEST METHOD

TEST CARRIED OUT IN ACCORDANCE WITH  
AS/NZS 4586:2004 (Appendix D)

Test Date: 16 January 2009

Location: Slip Resistance Laboratory

Sample Unfixed

Joint width: 0 mm

Surface structure:  Smooth  
 Profiled  
 Structured

### RESULTS

Mean overall acceptance angle: 10.4 °

Displacement space: not tested

### CLASSIFICATION:

Slip Resistance Assessment Group:

R 10 [LOW\*]

Displacement Space Assessment Group:

-

\* = CSIRO classification

### Comments:

These samples met the minimum requirements for the R10 slip resistance classification. Careful consideration should be used before using this floor sample in "wet" areas.

REPORT NO: 4686.2s Page 4 of 4  
 ISSUE DATE: 27 January 2009  
 MANUFACTURER: Dalsouple Australia Pty Ltd  
 TILE DESC: Endura rubber flooring, Black, sculptured profile  
 460x460mm

Date and Place 27 January 2009, Highett, Vic

Name, Title and Digital Signature:



**GERALD FISHER**  
**Laboratory Technician**  
 Tel: 61 3 92526414  
 Fax: 61 3 92526244  
 Email: Gerald.Fisher@csiro.au

**\*CSIRO recommended classification of Slip Resistance as determined from:  
 AS/NZS 4586: 2004 Slip Resistance Classification of New Pedestrian Surface Materials (Appendices A & D).**

Wet Pendulum Class	BPN 4S Rubber	CSIRO Class LOW	CSIRO Class MEDIUM	CSIRO Class HIGH
V	>54	54-57	58-61	>61
W	45-54	45-48	49-51	52-54
X	35-44	35-38	39-41	42-44
Y	25-34	25-28	29-31	32-34
Z	<25	<18	18-21	22-25
Oil Wet Ramp Class	Angle (degrees)	CSIRO Class LOW	CSIRO Class MEDIUM	CSIRO Class HIGH
R9	≥6 to <10	≥6 to 7.5	7.6 to 9	9.1 to 9.9
R10	≥10 to <19	≥10 to 12	12.1 to 15	15.1 to 18.9
R11	≥19 to <27	≥19 to 21	21.1 to 24	24.1 to 26.9
R12	≥27 to <35	≥27 to 29	29.1 to 32	32.1 to 34.9
R13	≥35	≥35 to 36	36.1 to 38	≥38.1

This table should not be read or relied upon without reference to the CSIRO/Standards Australia publication:  
 AS/NZS 4586 Slip Resistance Classification of New Pedestrian Surface Materials (Appendices A & D).

CSIRO has categorized the AS4586 classifications into sub-groups Low, Medium & High. The slip resistance test classification is still determined according to AS 4586 Australian Standard (Appendices A & D). The added information of Low, Medium and High allows professionals to make a better judgement of pedestrian floor requirements.